

Performance Data

Warranty (Years)	VLT (%)	UV Rejection (%)	Solvent Resistance	Stone Chip Resistance (SAE-J400)	Aging Test	Peel Strength (72h)	Peel Strength (20 min)	Gloss (60°)	Elongation at Break (ASTM D882)	Tensile Strength (MPa) (ASTM D882)	Liner (μm)	Adhesive (μm)	Top Coat (μm)	TPU (μm)	Thickness (μm)
5			NDE	Pass	NDE	>400 n/m	>400 n/m	>90	≥250	20	92	60	9	125	194
5			NDE	Pass	NDE	>400 n/m	>400 n/m	25	≥250	20	92	60	7	125	192
7			NDE	Pass	NDE	>400 n/m	>400 n/m	>85	>300	20	92	45	9	150	214
5			NDE	Pass	NDE	>400 n/m	>400 n/m	20	≥250	15	75	30	7	125	177