

Performance Data

	Thickness (μm)	TPU (μm)	Top Coat (μm)	Adhesive (μm)	Liner (μm)	Tensile Strength (MPa) (ASTM D882)	Elongation at Break (ASTM D882)	Gloss (60°)	Peel Strength (20 min)	Peel Strength (72h)	Aging Test	Stone Chip Resistance (SAE-J400)	Solvent Resistance	Warranty (Years)
Gold Shine	214	150	9	55	75	13	>300	>100	>400 n/m	>400 n/m	NDE	Pass	NDE	7
Moon Shine	214	150	9	55	75	13	>300	>90	>400 n/m	>400 n/m	NDE	Pass	NDE	7
Silver Shine	214	150	9	55	75	13	>300	>90	>400 n/m	>400 n/m	NDE	Pass	NDE	7
Champagne Diamond	199	150	9	40	75	15	>250	>90	>400 n/m	>400 n/m	NDE	Pass	NDE	7
Green Diamond	199	150	9	40	75	15	>250	>90	>400 n/m	>400 n/m	NDE	Pass	NDE	7
Blue Diamond	204	150	9	45	75	16	>250	>90	>400 n/m	>400 n/m	NDE	Pass	NDE	7
Pink Diamond	204	150	9	45	75	16	>250	>90	>400 n/m	>400 n/m	NDE	Pass	NDE	7
Purple Chameleon	206	150	9	47	75	15	>250	>90	>400 n/m	>400 n/m	NDE	Pass	NDE	7
Green Chameleon	206	150	9	47	75	15	>250	>90	>400 n/m	>400 n/m	NDE	Pass	NDE	7

